

# ZINGAFINISH

Zingafinish is a two pack polyurethane paint. Zingafinish gives a finish in most RAL colours with high hardness and elasticity. It does not yellow and is weather resistant and has good resistance to chemicals and water. Zingafinish is recommended as a finish coloured topcoat in a ZINGA system.

## PHYSICAL DATA AND TECHNICAL INFORMATION

### WET PRODUCT

Components	- Barium Sulphate - Magnesium Silicates - Outdoor resistant pigments (lead-free)
Binder	- Hydroxyacrylics - Aliphatic isocyanates
Density	1,33 kg/dm <sup>3</sup> ( $\pm 0,1$ Kg/dm <sup>3</sup> ) depending on the colour
Solid content	- 62% by volume ( $\pm 3\%$ ) - 74% by weight ( $\pm 3\%$ )
Type of thinner	Thinner 41 (preferably) or Zingasolv
VOC	355 g/L (= 273 g/Kg)

### DRY FILM

Colour	Most RAL colours
Gloss	60 ( $\pm 10$ )% Gardner 60°. Medium Gloss Grade, Level 5: Semi-Gloss (MPI)

### PACKING

4 L	Available
10 L	Available

### CONSERVATION

Pot life	$\pm 6$ hours at 20°C
Shelf life	3 years in the original, unopened package.
Storage	Store in a dry environment at temperatures between -20°C and +40°C.

## CONDITIONS

### SURFACE PREPARATION

When the waiting time between the successive coats is abnormally prolonged or in extremely polluted areas, the Zingafinished surface can become contaminated. All contamination that hampers the adhesion of the paint should be removed by appropriate means. Salt deposits or other water-soluble contamination should be removed with water and brush, water under high pressure or steam. Possible white rust on ZINGA should be removed with water and rigid nylon brush.

### ENVIRONMENTAL CONDITIONS DURING APPLICATION

Ambient temperature	- Minimum 0°C - Maximum 35°C
Relative humidity	- Minimum 30% - Maximum 85% - Do not apply on a damp or wet surface
Surface temperature	- Minimum 8°C - Minimum 3°C above the dew point - No visual presence of water or ice - Maximum 60°C

## APPLICATION INSTRUCTIONS

### GENERAL

Application methods	Zingafinish can be applied on top of ZINGA by brush and roller, conventional spray-gun or airless spraying.
Stripe coat	It is always recommended to treat corners, sharp edges, bolts and nuts before applying a uniform coat.
Cleaning	Cleaning of equipment with Zingasolv.
Mixing	Mix base paint and hardener BN 494 (mixing ratio: 5/1 in volume). Mixing errors result in deviating properties and differences in gloss. Therefore we advise to mix the complete contents of base paint and hardener.

### APPLICATION BY BRUSH AND ROLLER

Dilution	10 to 15% (v%) with Thinner 41 (or Zingasolv)
Type of brush or roller	Industrial round brush

### APPLICATION BY CONVENTIONAL SPRAY-GUN

Dilution	5 to 20% (v%) with Thinner 41 (or Zingasolv)
Pressure at the nozzle	3 to 5 bar
Nozzle opening	1,2 to 1,5 mm

### APPLICATION BY AIRLESS SPRAY

Dilution	0 to 10% (v%) with Thinner 41 (or Zingasolv)
Pressure at the nozzle	100 to 300 bar
Nozzle opening	0,017 to 0,024 inch

### APPLICATION ON ZINGA

Mist (tie) coat	20-30 µm DFT, diluted 10-15%
Full coat	2 hours after touch dry, DFT no more than 70-80 µm per layer

## OTHER INFORMATION

### COVERAGE AND CONSUMPTION

Theoretical coverage	- For 60 µm DFT: 11,00 m <sup>2</sup> /L - For 80 µm DFT: 8,25 m <sup>2</sup> /L
Theoretical consumption	- For 60 µm DFT: 0,09 L/m <sup>2</sup> - For 80 µm DFT: 0,12 L/m <sup>2</sup>
Practical coverage and consumption	Depends upon the roughness profile of the substrate and the application method.

### DRYING PROCESS AND OVERCOATING

Drying time	For 60 µm DFT at relative humidity of 75%: 20°C: Dustdry: 40 minutes Tackfree: 4 hours Dry: 12 hours
Overcoating	For 60 µm DFT at relative humidity of 75%: - 10°C: Minimum: 1 hour Maximum: 4 days - 20°C: Minimum: 30 minutes Maximum: 3 days - 30°C: Minimum: 30 minutes Maximum: 3 days Remark: At longer intervals a good cleaning is necessary to avoid intermediate coat contamination which could disturb the adherence of the next coat.



## TECHNICAL DATA SHEET

Ref.: Technische Fiches\TDS Zingafinish.EN

ZM-RE-PRO-04-B (02/09/14)

p. 4/4

[www.zinga.eu](http://www.zinga.eu)

30/10/15 - v1

### RECOMMENDED SYSTEM

ZINGA duplex system	Zingafinish can be applied directly onto ZINGA (apply with mist/full coat technique). <ul style="list-style-type: none"><li>• ZINGA 1 x 60-80 µm DFT + Zingafinish 1 x 60-80 µm DFT</li></ul>
ZINGA triplex system	For optimal gloss and extra barrier protection, a triplex system (with sealer) is recommended. <ul style="list-style-type: none"><li>• ZINGA 1 x 60-80 µm DFT + Zingalufer 1 x 80 µm DFT + Zingafinish 1 x 60-80 µm DFT</li><li>• ZINGA 1 x 60-80 µm DFT + Zingaceram HS 1 x 80 µm DFT + Zingafinish 1 x 60-80 µm DFT</li></ul>

For more specific and detailed recommendations concerning the application of Zingafinish, please contact a Zingametall representative. For detailed information about the health and safety hazards and precautions for use, refer to the Zingafinish safety data sheet.

---

The information on this sheet is merely indicative and is given to the best of our knowledge based on practical experience and testing. The conditions or methods of handling, storage, use or disposal of the product cannot be controlled by us and are therefore outside our responsibility. For these and other reasons we retain no liability in case of loss, damage or costs that are caused by or that are linked in any way to the handling, storage, use or disposal of the product. Any claim concerning deficiencies must be made within 15 days upon reception of the goods quoting the relevant batch number. We retain the right to change the formula if properties of the raw material are changed. This data sheet replaces all former specimens.